



Torlon[®] 7130

polyamide-imide

Torlon 7130 is an 30% carbon-fiber reinforced grade of polyamide-imide (PAI) resin. It offers high strength and modulus, exceptional creep resistance, and good fatigue resistance. It has thermal expansion characteristics similar to steel, and therefore excellent dimensional stability.

Torlon PAI has the highest strength and stiffness of any thermoplastic up to 275°C (525°F). It has outstanding resistance to wear, creep, and chemicals.

The potential applications for this resin include metal replacement, sliding vanes, aerospace parts, impellers, shrouds, pistons, and housings.

It is available in injection molding and extrusion (E) grades.

Typical Properties⁽¹⁾ by ASTM Test Methods

Property	Test Method	US Customary Units		SI Units	
MECHANICAL					
Tensile Strength	D 638	32.0	kpsi	221	MPa
	D 1708 ⁽²⁾	29.4	kpsi	203	MPa
Tensile Modulus	D 638	2,400	kpsi	16.5	GPa
	D 1708 ⁽²⁾	3,230	kpsi	22.3	GPa
Tensile Elongation	D 638	1.5	%	1.5	%
	D 1708 ⁽²⁾	6	%	6	%
Flexural Modulus	D 790				
	at 23°C (73°F)	2,880	kpsi	19.9	GPa
	at 232°C (450°F)	2,280	kpsi	15.7	GPa
Flexural Strength	D 790				
	at 23°C (73°F)	50.7	kpsi	350	MPa
	at 232°C (450°F)	25.2	kpsi	174	MPa
Izod Impact Strength, Notched	D 256	0.9	ft-lb/in	50	J/m
Izod Impact Strength, Unnotched	D 4812	6	ft-lb/in	320	J/m
Compressive Strength	D 695	36.9	kpsi	254	MPa
Compressive Modulus	D 695	1,430	kpsi	9.9	GPa

Continued on following page

Typical Properties⁽¹⁾ by ASTM Test Methods (continued)

Property	Test Method	US Customary Units		SI Units	
THERMAL					
Heat Deflection Temperature at 264 psi (1.8 MPA)	D 648	540	°F	282	°C
Thermal Conductivity	C 177	3.6	Btu in/hr- ft ² °F	0.52	W/mK
Coefficient of Thermal Expansion, flow direction	E 831	5	ppm/°F	9	ppm/°C
GENERAL					
Specific Gravity	D 792	1.48		1.48	
Water Absorption, 24 hours	D 570	0.26	%	0.26	%
Mold Shrinkage	D 955	0.0 - 0.15	%	0.0 - 0.15	%

⁽¹⁾ Property values for individual batches will vary within specification limits. Values shown are typical for uncolored resin; colorants may alter values.

⁽²⁾ ASTM Test Method D1708 has been used to measure the tensile properties of PAI and similar materials because the small test specimen conserved material.

Today the most widely used specimen is the Type 1 bar of ASTM D638. These D1708 values are included for historical purposes and they should not be compared to the D638 values.

Drying

Drying Torlon resin to a moisture content of 500 ppm or lower is required to avoid molding problems, such as brittle parts and foaming. The resin should be dried in a circulating air oven equipped with a desiccant system. Place the resin on drying trays in layers no more than 5 to 8 cm (2 to 3") deep. Minimum drying times are 3 hours at 175°C (350°F), 4 hours at 150°C (300°F), or 16 hours at 120°C (250°F). If drying at 175°C (350°F), limit drying time to 16 hours. Dessicant hopper dryers are recommended for the injection molding press.

Standard Packaging and Labeling

Torlon 7130 resin is packaged in lined cardboard boxes containing 25 kg (55.115 pounds) of material. Individual packages will be plainly marked with the product number, color, lot number, and net weight.

Injection Molding

The injection molding press should be equipped with a screw having a length to diameter (L/D) ratio between 18:1 and 24:1 and a compression ratio between 1:1 and 1.5:1. Check devices are not recommended.

Recommended barrel temperatures are 305°C (580°F) in the feed zone increasing to 370°C (700°F) at the nozzle. The mold temperature should be adjusted until the temperature of the surface measures between 200°C (390°F) and 215°C (420°F).

Set the injection pressure to achieve a rapid fill. On most machines, this will be near the maximum injection pressure available. Fill the entire mold with primary injection boost and then drop off to a hold pressure. Begin hold pressure at a high setting of 41 to 55 MPa (6,000 to 8,000 psi), for several seconds, then drop off to 21 to 35 MPa (3,000 to 5,000 psi), for the duration of the hold pressure sequence. This will help minimize or eliminate any internal porosity or sink. If part defects, such as blistering at the gate, color change and degradation, splay and surface delamination, or gas burning at the knit lines and vents, are encountered, the injection fill rate may be too high.

Use moderate back pressure, about 7 MPa (1,000 psi), and lower screw recovery speeds (50-100 rpm). Avoid intermittent feeding and screw slippage which can lead to overheating and possible polymer degradation.

Total cycle time should be as short as possible to reduce residence time in the barrel. Excessive residence time will cause an increase in melt viscosity, reducing flow.

Cycle time consistency is very important for successful molding for Torlon parts and automatic operation is highly recommended.

Molds should be designed for smooth part ejection, avoiding undercuts and providing adequate draft.

Heat Treatment (Post-Cure) After Molding

Torlon polymers are unique in that they are supplied at a relatively low molecular weight to facilitate processing, and the molded parts must be heat treated to achieve a high molecular weight and optimum properties. The heat treatment process is commonly called post-cure and involves placing the molded articles in a forced air oven and subjecting them to a series of elevated temperatures for specific times. Consult the Torlon polyamide-imide Molding Guide for standard post-cure cycles or contact your Solvay Advanced Polymers' representative for the recommended heat treatment program for post-curing your molded article.

For assistance with an emergency involving products of Solvay Advanced Polymers, such as a spill, leak, fire, or explosion, call day or night:

Emergency Health Information

USA +1.800.621.4590

International +1.770.772.8577

Emergency Spill Information

USA +1.800.424.9300 / +1.703.527.3887 (CHEMTREC)

Europe +44 208.762.8322 (CARECHEM)

China +86.10.5100.3039

All other Asian countries +65.633.44.177

For additional product information, technical assistance, and Material Safety Data Sheets (MSDS), call:

USA +1.800.621.4557 / +1.770.772.8760

Europe +49.211.5135.9000

Japan +81.3.5425.4300

China & Southeast Asia +86.21.5080.5080

World Headquarters

Solvay Advanced Polymers, LLC
4500 McGinnis Ferry Road
Alpharetta, Georgia 30005 USA
Phone: +1.800.621.4557 (USA Only)
+1.770.772.8760

SOLVAY
Advanced Polymers



MORE PLASTICS WITH MORE PERFORMANCE™

Solvay Advanced Polymers has many locations around the world. Please visit our website for the office nearest you, or email advancedpolymers@solvay.com for assistance. www.solvayadvancedpolymers.com

Material Safety Data Sheets (MSDS) for products of Solvay Advanced Polymers are available upon request from your sales representative or by emailing us at advancedpolymers@solvay.com. Always consult the appropriate MSDS before using any of our products.

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Advanced Polymers, LLC nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this information or its use. Only products designated as part of the Solviva™ family of biomaterials may be considered as candidates for implantable medical devices; Solvay Advanced Polymers does not allow or support the use of any other products in any implant applications. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The use of this product resides on the determination of the customer not Solvay Advanced Polymers. The customer must determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Advanced Polymers reserves the right to make additions, deletions, or modifications to the information at any time without prior notification.

All trademarks and registered trademarks are the property of Solvay Advanced Polymers, LLC, an affiliate of Solvay SA.
© 2009 Solvay Advanced Polymers, LLC. All rights reserved.